



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C01B 33/00	A2	(11) International Publication Number: WO 99/36356 (43) International Publication Date: 22 July 1999 (22.07.99)
(21) International Application Number: PCT/US99/00166 (22) International Filing Date: 13 January 1999 (13.01.99) (30) Priority Data: 60/071,359 15 January 1998 (15.01.98) US (71) Applicant: CABOT CORPORATION [US/US]; 75 State Street, Boston, MA 02109-1806 (US). (72) Inventors: MENON, Vinayan, C.; 801 Locust Place N.E. #2060 H, Albuquerque, NM 87102 (US). WALLACE, Stephen; 8426 Yeager Drive N.E., Albuquerque, NM 87109-5134 (US). MASKARA, Alok; 801 Locust Place N.E. #1249 BB, Albuquerque, NM 87102 (US). SMITH, Douglas, M.; 215 Richmond S.E., Albuquerque, NM 87106 (US). KOEHLERT, Kenneth, C.; 1210 Dorchester Drive, Champaign, IL 61821 (US). (74) Agent: LANDO, Michelle, B.; Cabot Corporation, 157 Concord Road, P.O. Box 7001, Billerica, MA 01821-7001 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>Without international search report and to be republished upon receipt of that report.</i>

(54) Title: POLYFUNCTIONAL ORGANOSILANE TREATMENT OF SILICA**(57) Abstract**

The present invention provides a method of treating silica wherein silica is reacted with a di- or tri-functional organosilane in an aqueous acid medium to provide a crude organosilane-capped silica product containing organosilicon impurities. The organosilicon impurities are extracted from the crude product with an organic liquid to provide a purified product consisting essentially of organosilane-capped silica. The purified product is dried to provide a dry organosilane-capped silica. The aqueous acid medium can include a displacing reagent which displaces at least one reactive functional group of the di- or tri-functional organosilane. The present invention further provides continuous methods of treating silica with di- and tri-functional organosilanes, wherein the organic liquid and/or the organosilicon impurities are recycled and reused.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

POLYFUNCTIONAL ORGANOSILANE TREATMENT OF SILICA

TECHNICAL FIELD OF THE INVENTION

The present invention relates to a method of
5 treating silica with organosilane reagents.

BACKGROUND OF THE INVENTION

Silica, an inorganic material having silicon dioxide
(SiO_2) as a basic structural unit, is useful in a wide
10 variety of commercial applications. Silica exists in a
variety of molecular forms, which include, for example,
monomers, dimers, oligomers, cyclic forms, and polymers.
In addition, silica can be amorphous, crystalline,
hydrated, solvated, or dry, and can exist in a variety of
15 particulate and aggregation states.

Amorphous silica can be formed by molecular
precipitation, for example, by cooling a supersaturated
solution, concentrating an undersaturated solution, or by
careful hydrolysis of a solution of a labile silica
20 precursor, such as a SiCl_4 , esters of silica, SiS_2 ,
 Si(OR)_4 , and the like, to provide a supersaturated
solution of Si(OH)_4 , from which precipitates amorphous
silica.

Pyrogenic, or "fumed silica", which has a particle
25 size from about 2-20 nm, is formed from the vapor phase.
For example, silica (usually sand) can be vaporized at
about 2000 °C and cooled to form anhydrous amorphous
silica particles. Alternatively, silica can be sublimed
at about 1500 °C in the presence of a reducing agent
30 (e.g., coke) to form SiO , which can be oxidized to form
particulate silica. Other methods of producing fumed
silica include, for example, oxidation of SiCl_4 at high
temperatures or burning SiCl_4 in the presence of methane
or hydrogen.

35 Silica solutions exhibit polymerization behavior,
resulting in the increase of Si-O-Si bonds and decrease
of Si-OH bonds. In an aqueous medium, amorphous silica

dissolves (and/or depolymerizes), forming $\text{Si}(\text{OH})_4$, which undergoes polymerization to form discrete particles with internal Si-O-Si bonds and external Si-OH bonds on the particle surface. Under certain conditions, the
5 polymeric silica particles thus formed will further associate to give chains and networks comprising the individual particles.

Generally, under neutral or alkaline conditions (pH 7 or greater), the particles tend to grow in size and
10 decrease in number, whereas under acidic conditions (pH < 7), the particles have a greater tendency to agglomerate to form chains, and eventually three dimensional networks. If salts are present which neutralize the charge produced on the particle surface, agglomeration of
15 particles will be more likely to occur under neutral or alkaline conditions.

The term "sol" refers to a stable dispersion of discrete, colloid-size particles of amorphous silica in aqueous solutions. Under the proper conditions, sols do
20 not gel or settle even after several years of storage, and may contain up to about 50% silica and particle sizes up to 300 nm, although particles larger than about 70 nm settle slowly. A sol can be formed, for example, by growing particles to a certain size in a weakly alkaline
25 solution, or by addition of dilute acid to a solution of sodium silicate (e.g., Na_2SiO_3) with rapid mixing, until the pH drops to about 8-10, followed by removal of Na^+ (e.g., by ion-exchange resin or electrodialysis). Silica sols, depending upon the type of silica, the particle
30 size, and the nature of the particles, can form gels under mildly acidic to strongly acidic conditions.

The term "gel" refers to a coherent, rigid, continuous three-dimensional network of particles of colloidal silica. Gels can be produced by the
35 aggregation of colloidal silica particles (typically under acidic conditions when neutralizing salts are absent) to form a three dimensional gel microstructure.

Whether a gel will form under a particular set of conditions, however, can depend on the silica properties, such as, for example, particle size and the nature of the particle surface. The term "hydrogel" refers to a gel in which the pores (spaces within the gel microstructure) are filled with water. Similarly, the term "alcogel" refers to a gel in which the pores are filled with an alcohol. When a gel is dried (liquid removed from the pores) by means in which the coherent gel microstructure collapses (e.g., by solvent evaporation), a relatively high density collapsed powder, or "xerogel", is formed. In contrast, when a gel is dried by means in which the gel microstructure is preserved (e.g., supercritical drying as described in U.S. Patent 3,652,214), a low density "aerogel" is formed. Silica aerogels have very unusual and highly desirable properties such as, for example, optical transparency, extremely low density, and unprecedented low thermal conductivity. See Herrmann et al., *Journal of Non-Crystalline Solids*, 186, 380-387 (1995). Silica aerogels are useful in a wide variety of applications which include, for example, thermal insulators and reinforcing fillers for elastomers. Although raw material costs are very low, economically feasible processes for producing aerogels have been pursued unsuccessfully for decades.

It is known that the hydrophobic surface modification of silica can dramatically improve silica properties for use in numerous valuable commercial applications. U.S. Patent 3,015,645 ("Tyler") discloses that hydrophobic silicon powders prepared by reacting silica with hydrophobing agents, such as organosilicon halides, can produce superior reinforcing fillers for siloxane elastomers. U.S. Patent 3,122,520 ("Lentz") discloses an improved method of preparing Tyler-type organosilated silica fillers, which improvement involves subjecting a silica sol to a strong acid at low pH (less than 1) and high temperatures prior to introducing the

hydrophobing agent. U.S. Patent 2,786,042 ("Iler") discloses hydrophobic organic surface-modified silica, organosols, and preparation methods thereof.

Although strongly acidic conditions purportedly
5 improve the surface modification of silica, there are serious drawbacks to using strong acids in the production of low density organic-modified silica, particularly when the modifying agent is a reactive organosilane. When trimethylchlorosilane (TMCS) is used as the organic
10 modifying reagent, the formation of undesirable reaction by-products can be controlled to a certain extent under strongly acidic conditions. However, when lower cost di- or tri-functional organosilane modifying agents such as dimethyldichlorosilane (DMDCS) or methyltrichlorosilane
15 (MTCS) are used under strongly acidic conditions, they tend to form by-products, polymerize, and/or crosslink with other silanes, resulting in a higher density product, which is undesirable. Such side reactions can result in poor product quality, low yield, and
20 inefficient utilization of di- and tri-functional organosilane surface modifying agents. These shortcomings pose a substantial barrier to the commercialization of processes related to the production of surface-modified silica with di- and tri-functional
25 organosilane surface modifying agents.

In view of the foregoing problems, there exists a need for an improved method for the surface modification of silica using di- and tri-functional organosilane surface modifying agents. The present invention provides
30 such a method. These and other advantages of the present invention, as well as additional inventive features, will be apparent from the description of the invention provided herein.

35

BRIEF SUMMARY OF THE INVENTION

The present invention provides a method of treating silica wherein silica is reacted with a di- or tri-

functional organosilane in an aqueous acid medium to provide a crude organosilane-capped silica product containing organosilicon impurities. The organosilicon impurities are extracted from the crude product with an organic liquid to provide a purified product consisting essentially of organosilane-capped silica. The purified product is dried to provide a dry organosilane-capped silica. The aqueous acid medium can include a displacing reagent which displaces at least one reactive functional group of the di- or tri-functional organosilane.

The present invention further provides continuous methods of treating silica with di- and tri-functional organosilanes, wherein the organic liquid and/or the organosilicon impurities are recycled and reused.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention provides a method of treating silica wherein silica is reacted with a di- or tri-functional organosilane in an aqueous acid medium to provide a crude organosilane-capped silica product containing organosilicon impurities. The organosilicon impurities are extracted from the crude product with an organic liquid to provide a purified organosilane-capped silica product which is substantially free of organosilicon impurities. The purified product is then dried to provide a dry organosilane-capped silica which is substantially free of organosilicon impurities.

The present invention utilizes less costly di- or tri-functional organosilanes, sometimes herein referred to as "capping agents", for the treatment of silica. The term "organosilane-capped silica" refers to the reaction product of silica and the di- or tri-functional organosilane capping agent. As the term "organosilane-capped silica" suggests, the silanols of the silica form a covalent bond (i.e., are "capped") with the di- or tri-functional organosilane capping agent. The term "di- or tri-functional" refers to the number of reactive

functional groups on the organosilane capping agent which are capable of being displaced by a silica silanol, resulting in a covalent bond between the silica silanol and the silicon atom of the organosilane capping agent.

5 Thus, a di-functional organosilane has two reactive functional groups capable of being displaced by a silica silanol, and a tri-functional organosilane has three reactive functional groups.

Any suitable di- or tri-functional organosilane can
10 be utilized in the method of the present invention. Preferably, the capping agent is a di-functional organosilane of the formula $R_1R_2SiX_2$ or a tri-functional organosilane of the formula R_1SiX_3 , wherein R_1 and R_2 can be the same or different and each is C_1 - C_6 alkyl,
15 fluoroalkyl, aryl, or arylmethyl; and X is Cl , Br , I , or OR_4 , wherein R_4 is C_1 - C_4 alkyl. The di-functional capping agent is preferably a dialkyldichlorosilane, more preferably wherein R_1 and R_2 are C_1 - C_3 alkyl. Most preferably, the di-functional capping agent is
20 dimethyldichlorosilane (DMDCS). The tri-functional capping agent is preferably an alkyltrichlorosilane, more preferably wherein R_1 is C_1 - C_3 alkyl. Most preferably, the tri-functional capping agent is methyltrichlorosilane (MTCS). In addition to lower cost, the utilization of
25 polyfunctional organosilanes as reagents in the preparation of treated silica can be particularly beneficial from an environmental standpoint, particularly since MTCS is highly abundant in waste streams generated from silicone processes. Thus, the beneficial use of
30 such waste products is highly desirable.

Any suitable acid can be used in the method of the present invention. Preferably, the aqueous acid medium comprises a mineral acid, which is preferably hydrochloric acid or sulfuric acid. Most preferably, the
35 mineral acid is hydrochloric acid. The present invention utilizes high acid concentrations. Preferably the mineral acid is present in the aqueous acid medium in

concentrations greater than about 3 M, more preferably greater than about 10 M.

Unlike the monofunctional organosilanes (e.g. trimethylchlorosilane), di- and tri-functional silanes, particularly DMDCS and MTCS, are more reactive and tend to polymerize and crosslink under strongly acidic reaction conditions, resulting in the formation of polymeric organosilicon by-products. The formation of polymeric organosilicon by-products is difficult to control under strongly acidic conditions. Significant contamination of the organosilane-capped silica with the polymeric organosilicon impurities results in a product with undesirable qualities such as, for example, high density, low degree of "capping", and uncharacteristically low internal surface area. It has been discovered that significant contamination of the product with polymeric organosilicon impurities from di- or tri-functional organosilanes occurs during drying of the crude organosilane-capped silica, particularly in the presence of unreacted capping agents such as DMDCS and MTCS. Thus, even in applications where the treated silica product is isolated before the capping agent is totally consumed (where a lesser degree of surface coverage of the silica with the capping agent is desired), significant contamination can occur. Although not intending to be bound by any particular theory, it is believed that drying conditions promote further polymerization and crosslinking of the impurities (polymeric and unreacted) to the di- and tri-functional organosilanes which have already covalently bonded to the silanols on the silica surface.


In the method of the present invention, the polymeric and/or unreacted organosilicon impurities are removed from the crude organosilane-capped silica by extraction with an organic liquid prior to drying. Any suitable organic liquid can be used to perform the

extraction. Preferably, the organic liquid is hexamethyldisiloxane.

Any suitable volume can be used in the organic liquid extraction. The relative volume of organic liquid used in the extraction depends on many variables such as, for example, the amount of organosilicon impurities per unit volume of crude product, the nature of the organic liquid, and the solubility of the organosilicon impurities. A person of ordinary skill in the art will appreciate that techniques such as, for example, BET surface area values, BET C values, and thermal gravimetric analysis (TGA) can be utilized to detect the presence of polymeric substances in capped silica. BET values are typically based on measurement of N₂ adsorption at 77 K. In a typical adsorption experiment, the amount of nitrogen adsorbed at five different relative pressures over the range 0.05 to 0.25 is obtained and analyzed using the Brunauer-Emmett-Teller (BET) model, which can be found in Gregg, S.J. and Sing, K.S.W, "Adsorption, Surface Area and Porosity," p. 285, Academic Press, New York (1991). The BET model provides the surface area and C value for the powders. Generally, a significant TGA weight loss (greater than about 6 wt. %) in the dry organosilane-capped silica from about 200-400 °C indicates the presence of polymeric materials, whereas insignificant TGA weight loss (less than about 6 wt. %) from about 200-400 °C indicates low polymer content or the absence thereof. Preferably, the crude product is extracted with a sufficient volume of the organic liquid such that the dry organosilane-capped silica exhibits a TGA weight loss of less than about 6 wt. % from about 200 °C to about 400 °C.

To reduce the formation of polymeric organosilicon by-products, the aqueous acid medium can include a displacing reagent which displaces at least one reactive functional group of the di- or tri-functional organosilane to provide a less reactive organosilane

species. Any suitable displacing reagent can be utilized. The reaction between the displacing reagent and the di- or tri-functional organosilane need not proceed to completion. A person of ordinary skill in the art will appreciate that the extent of reaction of a particular displacing reagent with the reactive functional groups of a particular polyfunctional organosilane depends on variables such as, for example, the relative concentration and reactivity of both species. Although a distribution of different reactant species can form when the displacing reagent reacts with the di- or tri-functional organosilane, the net effect will be a lowered degree of polymerization. When, for example, the displacing reagent is an alcohol and MTCS is the polyfunctional organosilane, the distribution of possible reactant species can be illustrated by the following equation:



wherein CH_3SiCl_3 represents unreacted MTCS, $\text{CH}_3\text{Si(OR)Cl}_2$ represents the displacement of one reactive chloride, $\text{CH}_3\text{Si(OR)}_2\text{Cl}$ represents the displacement of two reactive chlorides, and $\text{CH}_3\text{Si(OR)}_3$ represents the displacement of all the available chlorides. The reactivity of alcohols with di- or tri-functional organosilanes decreases significantly with increasing steric hinderance about the alcohol hydroxyl. Thus, primary alcohols are significantly more reactive than secondary alcohols. For example, isopropanol can be used as an unreactive cosolvent at room temperature (see Example 1). Tertiary alcohols are the least reactive. Primary alcohols such as, for example, methanol and ethanol react more rapidly with di- or tri-functional organosilanes. Lower molecular weight primary alcohols react faster than higher molecular weight primary alcohols. Generally, the reactivity of the organosilicon species decreases with increasing alcohol substitution. Preferably, the

displacing reagent is a primary alcohol of the formula R-OH, wherein R is C₁-C₆ n-alkyl, more preferably C₁-C₃ n-alkyl, most preferably methanol.

Any suitable concentration of displacing reagent can be used in the present invention. When the displacing reagent is a mono-alcohol as described hereinbefore, the molar ratio of the di- or tri-functional organosilane to the mono-alcohol is preferably one to one less than the number of reactive functional groups of the di- or tri-functional organosilane. Thus, when the organosilane is a di-functional organosilane, the molar ratio of di-functional organosilane to mono-alcohol is preferably 1:1. Similarly, when the organosilane is a tri-functional organosilane, the molar ratio of the tri-functional organosilane to mono-alcohol is preferably 1:2. Optionally, the displacing reagent can be a diol wherein each displacing reagent molecule possesses two reactive sites (hydroxyls) capable of displacing a functional group on the di- or tri-functional organosilane. Preferably, the diol displacing reagent is ethylene glycol or propylene glycol. When the organosilane is a di-functional organosilane, the molar ratio of di-functional organosilane to diol preferably is 2:1. When the organosilane is a tri-functional organosilane, the molar ratio of tri-functional organosilane to diol preferably is 1:1.

Recycling of reagents is highly preferred, not only to further reduce costs and optimize reagent usage, but also to reduce the production of environmental wastes. The polymeric reaction by-products from the di- or tri-functional organosilane can be reused after being extracted from the crude product. Polymeric organosilicon by-products derived from di- or tri-functional organosilanes can be depolymerized in strong aqueous acid to regenerate a monomeric di- or tri-functional organosilane capping agent. For example, polymeric by-products from DMDCS or MTCS can be

depolymerized in about 3 to about 12 M HCl to regenerate DMDCS and MTCS, respectively. Preferably, the polymeric organosilicon reaction by-products are added back into the aqueous acid medium to regenerate a di- or tri-
5 functional organosilane, and reused as capping agents in subsequent reactions in the method of the present invention. When the recovered organosilicon impurities are unreacted di- or tri-functional organosilanes, they preferably are added back into the aqueous acid medium
10 and reused as capping agents in subsequent processes.

After extracting the organosilicon impurities from the organosilane-capped silica, the organic liquid can be recycled and reused in subsequent extractions. Any suitable recycling method can be utilized. Preferably,
15 the organic liquid is separated from the organosilicon impurities by distillation. If volatile impurities such as, for example, DMDCS or MTCS, are present and co-distill or azeotrope with the organic liquid during the recycling process, fractional distillation or multiple
20 distillations can be utilized to separate the organic liquid from the impurities in sufficient purity for reuse.

While the present inventive method can be performed in a batch process, the present invention further
25 provides a continuous process for the treatment of silica wherein the polymeric reaction by-products and/or the organic liquid are continuously separated, recovered, and reused as provided herein. The present invention also provides a continuous process for the treatment of
30 silica, wherein the unreacted di- or tri-functional organosilanes are continuously separated from the organic liquid, recovered, and reused as provided herein. Preferably, the polymeric reaction by-products, organic liquid, and unreacted di- or tri-functional organosilanes
35 are all recovered, reused, and recycled in a continuous process.

The following examples further illustrate the present invention but, of course, should not be construed as in any way limiting its scope.

5

EXAMPLE 1

This example illustrates a method of treating silica with a di- or tri-functional organosilane in an aqueous acid medium to provide a crude product of organosilane-capped silica containing polymeric organosilicon
10 impurities.

To 400 ml of an aqueous composition of fumed silica available from Cabot Corporation under the trademark Cab-O-Sil® HS5 (4 wt.% solids) was added 200 ml 12.5 M HCl, and the mixture was refluxed for 3 hours. After cooling
15 the mixture to room temperature, 200 ml of isopropanol was added, followed by the di-functional organosilane dimethyldichlorosilane (DMDCS) in a molar ratio of 1:1 (mole DMDCS : mole SiO₂). The mixture was stirred for 0.5 hours at room temperature, and 500 ml of heptane was
20 added. After the mixture separated into two layers, the organogel heptane layer was separated, washed with water, azeotroped, and dried to provide a crude product of DMDCS-capped silica containing polymeric organosilicon impurities. N₂ adsorption of the DMDCS-capped silica at
25 77 K was measured. The DMDCS-capped silica had a BET surface area of 81 m²/g and a C value of 12. The dry DMDCS-capped silica exhibited a significant weight loss between 200 °C and 400 °C, indicating the presence of polymeric organosilicon impurities.

30

EXAMPLE 2

This example illustrates the removal of polymeric organosilicon impurities from silica treated with a di- or tri-functional organosilane capping agent. A sample of
35 silica is treated with DMDCS according to Example 1 except, prior to drying, the crude product is extracted with hexamethyldisiloxane until the polymeric

organosilicon impurities are no longer present in the extracts by HPLC analysis. The product is then dried to provide purified DMDCS-capped silica which is substantially free of organosilicon impurities.

5

All of the references cited herein, including patents, patent applications, and publications, are hereby incorporated in their entireties by reference.

While this invention has been described with an
10 emphasis upon preferred embodiments, it will be obvious to those of ordinary skill in the art that variations of the preferred embodiments may be used and that it is intended that the invention may be practiced otherwise than as specifically described herein. Accordingly, this
15 invention includes all modifications encompassed within the spirit and scope of the invention as defined by the following claims.

WHAT IS CLAIMED IS:

1. A method of treating silica comprising:
 - (a) reacting silica with a di- or tri-
5 functional organosilane in an aqueous acid medium to provide a crude product comprising organosilane-capped silica and organosilicon impurities,
 - (b) extracting said organosilicon impurities from said crude product with an organic liquid to provide
10 a purified product consisting essentially of organosilane-capped silica, and
 - (c) drying said purified product to provide a dry organosilane-capped silica.
2. The method of claim 1, wherein said di-
15 functional organosilane is dimethyldichlorosilane.
3. The method of claim 1, wherein said tri-functional organosilane is trichloromethylsilane.
4. The method of claim 1, wherein said aqueous acid medium comprises a mineral acid selected from the
20 group consisting of hydrochloric acid and sulfuric acid.
5. The method of claim 4, wherein said mineral acid is hydrochloric acid.
6. The method of claim 5, wherein the concentration of said mineral acid in said aqueous acid
25 medium is greater than about 3 M.
7. The method of claim 5, wherein the concentration of said mineral acid in said aqueous acid medium is greater than about 10 M.
8. The method of claim 1, wherein said
30 organosilicon impurities comprise polymeric reaction by-products from said di- or tri-functional organosilane.
9. The method of claim 1, wherein said organosilicon impurities comprise unreacted di- or tri-functional organosilane.
- 35 10. The method of claim 1, wherein said organic liquid is hexamethyldisiloxane.

11. The method of claim 1, wherein said dry organosilane-capped silica has a thermal gravimetric analysis (TGA) weight loss of less than about 6 wt. % from about 200 °C to about 400 °C.

5 12. The method of claim 1, wherein said aqueous acid medium includes a displacing reagent which displaces at least one reactive functional group of said di- or tri-functional organosilane.

10 13. The method of claim 12, wherein said displacing reagent is an alcohol of the formula R-OH, wherein R is C₁-C₆ n-alkyl.

14. The method of claim 13, wherein said alcohol is methanol.

15 15. The method of claim 13, wherein the molar ratio of said di- or tri-functional organosilane to said alcohol is one to one less than the number of reactive functional groups of said di- or tri-functional organosilane.

20 16. The method of claim 13, wherein said organosilane is a di-functional organosilane, and the molar ratio of said di-functional organosilane to said alcohol is 1:1.

25 17. The method of claim 13, wherein said organosilane is a tri-functional organosilane, and the molar ratio of said tri-functional organosilane to said alcohol is 1:2.

18. The method of claim 12, wherein said displacing reagent is an alcohol selected from the group consisting of ethylene glycol and propylene glycol.

30 19. The method of claim 18, wherein said organosilane is a tri-functional organosilane, and the molar ratio of said tri-functional organosilane to said displacing reagent is 1:1.

35 20. The method of claim 1, wherein said organic liquid is recycled after extracting said organosilicon impurities and reused in step (a).

21. The method of claim 8, wherein said polymeric reaction by-products from said di- or tri-functional organosilane are added to said aqueous acid medium to regenerate a di- or tri-functional organosilane and reused in step (a).

22. The method of claim 21, wherein said organic liquid is recycled and reused in step (a).

23. The method of claim 22, wherein said organic liquid is hexamethyldisiloxane.

24. The method of claim 9, wherein said unreacted di- or tri-functional organosilane is added to said aqueous acid medium and reused in step (a).

25. The method of claim 24, wherein said organic liquid is recycled and reused in step (a).

26. The method of claim 25, wherein said organic liquid is hexamethyldisiloxane.

27. The method of claim 22, wherein said method is a continuous process.

28. The method of claim 25, wherein said method is a continuous process.



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶ : C09C 1/30, C01B 33/18	A3	(11) International Publication Number: WO 99/36356 (43) International Publication Date: 22 July 1999 (22.07.99)
(21) International Application Number: PCT/US99/00166 (22) International Filing Date: 13 January 1999 (13.01.99) (30) Priority Data: 60/071,359 15 January 1998 (15.01.98) US (71) Applicant: CABOT CORPORATION [US/US]; 75 State Street, Boston, MA 02109-1806 (US). (72) Inventors: MENON, Vinayan, C.; 801 Locust Place N.E. #2060 H, Albuquerque, NM 87102 (US). WALLACE, Stephen; 8426 Yeager Drive N.E., Albuquerque, NM 87109-5134 (US). MASKARA, Alok; 801 Locust Place N.E. #1249 BB, Albuquerque, NM 87102 (US). SMITH, Douglas, M.; 215 Richmond S.E., Albuquerque, NM 87106 (US). KOEHLERT, Kenneth, C.; 1210 Dorchester Drive, Champaign, IL 61821 (US). (74) Agent: LANDO, Michelle, B.; Cabot Corporation, 157 Concord Road, P.O. Box 7001, Billerica, MA 01821-7001 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> (88) Date of publication of the international search report: 9 December 1999 (09.12.99)
(54) Title: POLYFUNCTIONAL ORGANOSILANE TREATMENT OF SILICA (57) Abstract <p>The present invention provides a method of treating silica wherein silica is reacted with a di- or tri-functional organosilane in an aqueous acid medium to provide a crude organosilane-capped silica product containing organosilicon impurities. The organosilicon impurities are extracted from the crude product with an organic liquid to provide a purified product consisting essentially of organosilane-capped silica. The purified product is dried to provide a dry organosilane-capped silica. The aqueous acid medium can include a displacing reagent which displaces at least one reactive functional group of the di- or tri-functional organosilane. The present invention further provides continuous methods of treating silica with di- and tri-functional organosilanes, wherein the organic liquid and/or the organosilicon impurities are recycled and reused.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09C1/30 B33/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09C C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 708 069 A (BURNS GARY THOMAS ET AL) 13 January 1998 (1998-01-13) the whole document	1-5, 10, 12, 13
E	EP 0 900 829 A (DOW CORNING) 10 March 1999 (1999-03-10) claims 1, 8 column 1, line 1 - line 16 column 3, line 38 - column 4, line 2 column 4, line 38 - column 5, line 17 column 5, line 29 - line 45 column 6, line 23 - line 33	1, 2, 4, 5, 10, 12, 13
E	EP 0 928 818 A (DOW CORNING) 14 July 1999 (1999-07-14) the whole document	1, 2, 4, 5, 10, 12, 13

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

20 October 1999

Date of mailing of the international search report

29/10/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Rigondaud, B

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>DATABASE WPI Section Ch, Week 199015 Derwent Publications Ltd., London, GB; Class A60, AN 1990-110367 XP002119601 & JP 02 059417 A (SHINETSU CHEM IND CO LTD), 28 February 1990 (1990-02-28) abstract</p>	1
A	<p>GB 682 574 A (DOW CORNING LIMITED) the whole document</p>	1
A	<p>GB 907 179 A (DOW CORNING LIMITED) the whole document</p>	1

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US 5708069	A	13-01-1998	AU	6436098 A	09-09-1998
			WO	9837016 A	27-08-1998
EP 0900829	A	10-03-1999	US	5908660 A	01-06-1999
			JP	11157825 A	15-06-1999
EP 0928818	A	14-07-1999	US	5919298 A	06-07-1999
JP 2059417	A	28-02-1990	JP	1779106 C	13-08-1993
			JP	4070253 B	10-11-1992
GB 682574	A		NONE		
GB 907179	A		NONE		